

## Technical Information

<b>Product name:</b>	<b><u>G-8475-500</u></b>																					
<b>Product description:</b>	G-8475-500 is a formulated elastomeric polyurethane system, with excellent resistance to weather and long lifespan. This elastomer has excellent adhesion properties.																					
<b>Material properties and processing information:</b>	<p><b>Mixing ratio A : B (by weight) 100:40</b></p> <p><b>Lab reactivity profile</b> measured at 22°C:</p> <table border="0"> <tr> <td>Free rise density.....</td> <td>500 ± 100</td> <td>Kg/m<sup>3</sup></td> </tr> <tr> <td>Cream time.....</td> <td>35 ± 10</td> <td>sec</td> </tr> <tr> <td>Rise time.....</td> <td>120 ± 30</td> <td>sec</td> </tr> <tr> <td>Specific gravity part A.....</td> <td>1.1 ± 0.1</td> <td>g/ml</td> </tr> <tr> <td>Specific gravity part B.....</td> <td>1.22 ± 0.2</td> <td>g/ml</td> </tr> <tr> <td>Viscosity part A.....</td> <td>800 ± 100</td> <td>cP</td> </tr> <tr> <td>Viscosity part B.....</td> <td>300 ± 100</td> <td>cP</td> </tr> </table>	Free rise density.....	500 ± 100	Kg/m <sup>3</sup>	Cream time.....	35 ± 10	sec	Rise time.....	120 ± 30	sec	Specific gravity part A.....	1.1 ± 0.1	g/ml	Specific gravity part B.....	1.22 ± 0.2	g/ml	Viscosity part A.....	800 ± 100	cP	Viscosity part B.....	300 ± 100	cP
Free rise density.....	500 ± 100	Kg/m <sup>3</sup>																				
Cream time.....	35 ± 10	sec																				
Rise time.....	120 ± 30	sec																				
Specific gravity part A.....	1.1 ± 0.1	g/ml																				
Specific gravity part B.....	1.22 ± 0.2	g/ml																				
Viscosity part A.....	800 ± 100	cP																				
Viscosity part B.....	300 ± 100	cP																				
<b>Cured properties:</b>	<table border="0"> <tr> <td>Final applied density.....</td> <td>700 ± 100</td> <td>Kg/m<sup>3</sup></td> </tr> <tr> <td>Hardness.....</td> <td>70 ± 10</td> <td>ShA</td> </tr> <tr> <td>Elongation at break.....</td> <td>100 ± 50</td> <td>%</td> </tr> <tr> <td>Adhesion to appropriate steel.....</td> <td>good</td> <td></td> </tr> </table>	Final applied density.....	700 ± 100	Kg/m <sup>3</sup>	Hardness.....	70 ± 10	ShA	Elongation at break.....	100 ± 50	%	Adhesion to appropriate steel.....	good										
Final applied density.....	700 ± 100	Kg/m <sup>3</sup>																				
Hardness.....	70 ± 10	ShA																				
Elongation at break.....	100 ± 50	%																				
Adhesion to appropriate steel.....	good																					
<b>Packing:</b>	<table border="0"> <tr> <td>Component A.....</td> <td>5, 20, 200</td> <td>Kg</td> </tr> <tr> <td>Component B.....</td> <td>5, 20, 200</td> <td>Kg</td> </tr> </table>	Component A.....	5, 20, 200	Kg	Component B.....	5, 20, 200	Kg															
Component A.....	5, 20, 200	Kg																				
Component B.....	5, 20, 200	Kg																				
<b>Storage:</b>	G-8475-500 has a retest period of 3 months at room temperature (25°C) in well-sealed 200 liter steel containers. Smaller/other packaging have shorter retest period. Do not allow moisture to enter.																					
<b>Safety measures:</b>	See MSDS																					

Disclaimer: The specification and properties are given to the best of our knowledge and experience. As a result of wide range of possible applications and changing processing conditions, we cannot be responsible for the results received by the end user and/or any third party concerned.